

CHEUNG KEE CANVAS LTD
G/F, 352, RECLAMATION STREET, KOWLOON, HONG KONG.


The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description : BS476 PVC TARPAULIN
 SGS Ref. No. : AJFS1911012129FF
 Style / Item No. : CK 2020
 Sample Receiving Date : Nov.25, 2019
 Test Performing Date : Nov.25, 2019 to Dec.03, 2019

Test Result Summary

Test(s) Requested	Result(s)	Comments
BS 476 Part 7:1997 Incorporating Corrigendum No.1:2014 "Fire tests on building materials and structures Part 7: Method of test to determine the classification of the surface spread of flame of products".	Please refer to the following page(s)	/
For further details, please refer to the following page(s)		

Signed for and on behalf of
Shunde Branch
SGS-CSTC Co., Ltd.



Cindy Xie
Approved signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's Instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

SDHL 174633

I. Test conducted

This test was performed in accordance with the procedure specified in BS 476 Part 7:1997 *Incorporating Corrigendum No.1:2014* "Fire tests on building materials and structures Part 7. Method of test to determine the classification of the surface spread of flame of products".

II. Sample details

Sample description	One sample of fabric
Density	About 354g/m ²
Color	Green
Specimen size	885mm×270mm

III. Test details

Conditioning of specimens:	Prior to testing, the sample was conditioned to constant mass at a temperature of 23 ± 2 °C, and a relative humidity of 50 ± 10 %, and maintained in this condition until required for testing.
Exposed Face:	One surface

Irradiance along horizontal reference line on the calibration board

Distance along reference line from inside edge of specimen holder	Irradiance kW/m ²		
	Specified	Min.	Max.
mm			
75	32.5	32.0	33.0
225	21.0	20.5	21.5
375	14.5	14.0	15.0
525	10.0	9.5	10.5
675	7.0	6.5	7.5
825	5.0	4.5	5.5

To be continued....

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

SDHL 174634



IV. Test results

SPECIMEN No.	1	2	3	4	5	6
Distance (mm)	Time to travel to indicated distance (minutes:seconds)					
75	0:04	0:03	0:05	0:04	0:03	0:03
165	--	--	--	--	--	--
190	--	--	--	--	--	--
215	--	--	--	--	--	--
240	--	--	--	--	--	--
265	--	--	--	--	--	--
290	--	--	--	--	--	--
375	--	--	--	--	--	--
455	--	--	--	--	--	--
500	--	--	--	--	--	--
525	--	--	--	--	--	--
600	--	--	--	--	--	--
675	--	--	--	--	--	--
710	--	--	--	--	--	--
750	--	--	--	--	--	--
785	--	--	--	--	--	--
825	--	--	--	--	--	--
Maximum distance traveled at 1.5 minutes (mm)	90	110	100	90	130	120
Maximum distance traveled during the whole test (mm)	90	110	100	90	130	120
Time to reach maximum distance traveled	0:08	0:09	0:10	0:08	0:09	0:10

Note: 1. "--" Not reached the reference line

2. Six specimens are usually tested. If the test on any specimen is deemed to be invalid, as defined in the standard, it is permissible for up to a maximum of nine specimens to be tested in order to obtain the six valid test results.

The classification limits specified in BS 476-7:1997 Incorporating Corrigendum No.1:2014 are given in Appendix 1.

Observations during test: None

To be continued....



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/terms-and-conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

SDHL 174635

Criteria for classification:

If the prefix "D" or suffix "R" or "Y" is included in the classification, this indicates that the results should be treated with caution. An explanation of the reason for prefix and suffixes is given in Appendix 2

Appendix 1 Classification of spread of flame

Classification	Spread of flame at 1.5 min		Final spread of flame	
	Limit (mm)	Limit for one specimen in sample(mm)	Limit (mm)	Limit for one specimen in sample(mm)
Class 1	165	165+25	165	165+25
Class 2	215	215+25	455	455+45
Class 3	265	265+25	710	710+75
Class 4	Exceeding the limits for class 3			

Appendix 2 Explanation of prefix and suffixes which may be added to the classification

1. A suffix R is added to the classification if more than six specimens are required in order to obtain six valid test results (e.g. class 2R).
2. A prefix D is added to the classification of any product which does not conform to the surface characteristics specified in the standard and has therefore been tested in a modified form (e.g. class D3).
3. A suffix Y shall be added to the classification if any softening and/or other behaviour that may affect the flame spread occurs.

Classification: In accordance with the class definitions given in BS 476 Part 7:1997 *Incorporating Corrigendum No. 1:2014*, the tested sample is classified as **Class 1**.

Statements:

This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test. They are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test results relate only to the specimens of the product in the form in which were tested. Small differences in the composition or thickness of the product may significantly affect the performance during the test and may therefore invalidate the test results. Care should be taken to ensure that any product, which is supplied or used, is fully represented by the specimens, which were tested.

To be continued....

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/terms-and-conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

SDHL 174636



SGS-CSI Standards Technical Services Co., Ltd.
Shunde Branch

1/F, 1st Building European Industrial Park, No.1 Shunhe South Road, Wusha Section, Daikang Town, Shunde, Foshan, Guangdong, China 528333 t (86-757)22805888 f (86-757)22805858 www.sgsgroup.com.cn
中国·广东·佛山市顺德区大良街道办事处五沙顺和南路1号欧洲工业园一号楼首层 邮编: 528333 t (86-757)22805888 f (86-757)22805858 e sgs.china@sgs.com

Photo Appendix:



Remark: This test was subcontracted to SGS-CSTC Co., Ltd. Anji Branch.

End of Report

Attention: To check the authenticity of testing inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com

