

Test Report No.SDHL2304007150HI Date: May 09, 2023 Page 1 of 3

CHEUNG KEE CANVAS LTD G/F,352,RECLAMATION STREET,KOWLOON,HONG KONG

Sample Description : PVC TARPAUILN

Item No. : CK 2007

As above test item and its relevant information regarding to the submission are provided and confirmed by the applicant. SGS is not liable to either the test item or its relevant information, in terms of the accuracy, suitability, reliability or/and integrity accordingly.

\*\*\*\*\*\*

SGS Ref No. : SDFS2304002349FF

Sample Receiving Date : Apr 28, 2023

Test Performing Date : Apr 28, 2023 to May 09, 2023

Test Performed : Selected test(s) as requested by applicant

### **Test Result Summary**

No.	Test(s) Requested	Result(s)	Comments				
	BS 5867-2:2008 Fabrics for curtains, drapes and	Defeate most	No precondition and				
1	window blinds—Part 2: Flammability requirements—	Refer to next	cleansing procedure as				
	Specification Clause 6 Type B	page(s)	per client's requirement				
For further details, please refer to the following page(s)							

Signed for and on behalf of SGS-CSTC Standards Technical Services Co., Ltd. Shunde Branch

Peter Zhao

**Authorized Signatory** 





Inless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printe overleaf, available on request or accessible at http://www.sps.com/en/Terms-and-Conditions.apx and, for electronic format documents ubject to Terms and Conditions frems-e-Documents at http://www.sps.com/en/Terms-and-Conditions/Terms-e-Document.apx itention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein, Any holder of this document is divised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of illentis instructions, if any. The Company's sole responsibility is to its Client and this document does not excerted parties to except in full, without prior written approval of the Company, Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the w. Unless otherwise stated the south is the company of the company. Any unauthorized alteration, forgery or falsification of the content or succept in the company is unlawful and offenders may be prosecuted to the fullest extent of the w. Unless otherwise stated the south is check the authenticity of testing / inspection report & certificate, please contact as at telephone: (86-755) 830 ktetonion. The company is a telephone in the company of the certificate, please contact as telephone (86-755) 830 ktetonion.

| 「Fi-Baing\_Empsenthatris Prix Nut | Sturie South Rout|| Made Sectors, Daing Town, Sunte, Frotes (Jeangtong, Dine 528333 t (86 – 757)22805888 f (86 – 757)22805888 www.sgs.group.com.cn 中国・广东・傳山市原植区大良街道亦事处五沙順和南路1号欧洲工业园一号厂房首层 邮集:528333 t (86 – 757)22805888 f (86 – 757)22805888 e sgs.china@sgs.com



**Test Report** 

No.SDHL2304007150HI

Page 2 of 3

Date: May 09, 2023

<u>Test Conducted:</u>
This test is conducted accordance with BS 5867-2:2008 Fabrics for curtains, drapes and window blinds—Part 2: Flammability requirements—Specification Clause 6 Type B.

### I Sample Details

Materials / Weight	Textile / 318g/m²							
II Precondition and Test Condition								
Testing Enclosure (fume cupboard /room)	25.9 ℃	RH 62 %						
Gas used	Butane gas							

### **III Test Results**

Clause	Requirement	Result	
4 Sampling	A sample shall be taken of sufficient size to provide the required test specimens from each finishing batch or from at least every 5000m.		
4 Gampling	Retesting shall be carried out where there is any major alteration to a fabric specification.		
5 Durability of treatment	The sample shall also be submitted to the appropriate cleansing or wetting procedure specified in BS EN ISO 10528, BS EN 1021-1 or BS 5651, depending	NO*	
6 Type B	on the specified performance or the information given on the care of the fabric.  The test methods as described in BS EN ISO 15025:2002, Procedure "A" (surface ignition) shall be used.  Requirement:  No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge of the sample. If any part of any hole or any part of the lowest boundary of any flame, reaches the top edge or either vertical edge, or if there is any separation of any flaming debris droplets in the testing of one specimen, a further six specimens shall be tested. If all six new specimens comply with the above requirements, the fabric shall be deemed to conform to the requirements of type "B" of this British Standard.	See Annex I	
7 Marking	<ul> <li>Except for fabrics used by the Department of Health, for which particular marking requirements are given in the purchase contract, a fabric for which conformity to the requirements of this British Standard is claimed shall be supplied with the following information: <ol> <li>Manufacture's name, trademark or other identifying mark.</li> <li>The statement 'Flammability complies with the requirements of BS 5867-2:2008, adding type "A", type "B" or type "C" as appropriate.</li> <li>A statement as to the durability of the fire resistance of the fabric.</li> <li>Instructions on any special precautions to be taken concerning care (including cleansing) of the curtain, drape or window blind to be manufactured from the fabric, preferably using an appropriate care labeling symbol in accordance with BS EN ISO 3758 and taking account of the durability procedure specified in Clause 5. If the fabric is unsuitable for cleansing this shall be stated.</li> <li>If the fabric has a non-durable finish, it shall be labelled as specified in Clause5. Any finished assembly of fabric having a non-durable finish shall be permanently labelled in the same way.</li> </ol> </li></ul>	N/P	

Remark: N/P - Not provided. \*- As the client's requirement.





**Test Report** 

No.SDHL2304007150HI

Date: May 09, 2023

Page 3 of 3

# **Annex I: Details of Test**

The test specified in BS EN ISO 15025:2002 Protective clothing—Protection against heat and flame—Method of test for limited flame spread (Surface ignition).

#### **Test Results:**


Apply the flame to the specimen for 15s

**Before Cleaning** 

Particulars -		Machine direction		Cross direction		
		2	3	4	5	6
Any part of any hole reach the top edge or either vertical edge (Yes / No)	NO	NO	NO	NO	NO	NO
Any part of the lowest boundary of any flame reach the top edge or either vertical edge (Yes / No)	NO	NO	NO	NO	NO	NO
Flaming debris (Yes / No)	NO	NO	NO	NO	NO	NO

Note: This document cannot be reproduced except full, without prior written approval of the Company.

## **Photo Appendix:**



\*\*\*End of Report\*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Tems-and-Conditions.aspx.and, for electronic Port at course, and the control of the control o